



PRODUCT DATA

WELLSEAL JOINTING COMPOUND

DESCRIPTION

Wellseal Jointing Compound is formulated to give the best possible sealing performance under a wide variety of conditions. Commonly used to seal Aluminum cylinder heads and transmission boxes. It is used to seal threaded connections as well as flat-faced joints and can be used with or without a gasket, depending upon the design of the assembly.

Wellseal Jointing Compound is highly resistant to the majority of commonly used field, lubricants and coolants and is non-corrosive and free from abrasive fillers.

PROPERTIES

Colour	Transparent Brown Liquid
Solvent Content	48.5% - 52.5%
Viscosity @ 20°C, Brookfield RVT, Spindle N°3	2.5 rpm - 10,500 ± 200cp
Flash Point	Non-flammable
Temperature Range	-55°C to +200°C
Specific Gravity	1.26

SPECIFICATION

Wellseal is available, to order, made to meet the requirements of specification AFS 1670 and DTD 900 / 6054.

APPLICATION

The compound is applied direct from the container to the previously cleaned surface and spread out in a thin, even film. Application to both surfaces is preferred.

HANDLING PRECAUTIONS

Wellseal Jointing Compound is non-flammable, but contains a solvent that may cause irritation on skin or eye contact. It should be used in a well-ventilated area and inhalation of the vapour should be avoided as far as possible. Under no circumstances should smoking be allowed where Wellseal is being used.

STORAGE

No special precautions are necessary other than storage at normal ambient temperatures.

SHELF LIFE

At least 3 years in unopened containers.

PACKAGING

100ml tubes, 500ml conical cans, 5 litre cans.

Kommerling UK Limited

27 Riverside Way, Uxbridge, Middlesex UB8 2YF, England

Tel: 01895 465600 Fax: 01895 465617

Every endeavour has been made to ensure that the information given herein is true and reliable but is given only for the guidance of our customers. The company cannot accept any responsibility for loss or damage or infringement of patent rights that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of the products with their own tests. Any dimensions shown are approximate.